

Encapsulation of “type c” asbestos cement artefacts and subsequent placement of paired panels in direct contact with the asbestos cement structure

LV27_SA_EN_R2-0517

APPLICATION DATA SHEET

Encapsulation of “type c” asbestos cement artefacts and subsequent placement of paired panels in direct contact with the asbestos cement structure, by:

- 1. preparation of the substrates;**
- 2. encapsulation.**

1) PREPARATION OF THE SUBSTRATES

The use of the products will be carried out with suitable equipment, by qualified personnel and according to the laws.

The cleaning of the substrate will be done with appropriate techniques in order to eliminate dust, grease, old paints and everything that could compromise subsequent procedures.

2) ENCAPSULATION

Spraying of single-component reinforcing resin **Kimicover BLINDO**.

The resin, which has strong characteristics of adherence, resistance to sudden changes in temperature, will be applied in a single layer for an average consumption of about 0.350 kg/m², after being diluted with the 10-15% of drinking water.

The total thickness of the encapsulating coating must not be less than 200 microns and must not exceed 600 microns.

Subsequent placement of suitable paired panels in direct contact with the structure.