

Stucco skimming of interior facades or walls with a mineral smooth finish

LV38_SA_EN_R2-0517

APPLICATION DATA SHEET

Stucco skimming of interior facades or walls with a mineral smooth finish by:

1. preparation of the substrate;
2. skimming.

1) PREPARATION OF THE SUBSTRATE

In case of old but compact plasters, clean them to remove old paints and flimsy parts (which could compromise the good anchoring) with a suitable pressure washing and, where necessary, with mechanical abrasions, in order to eliminate old paints and inconsistent parts that could compromise the good anchoring of the subsequent layers. On new plaster, wait until it is completely cured and check that it is compact and clean.

Then wet the substrate to saturation.

2) SKIMMING

Apply the product in two layers with a metal spatula with ready to use lime-based filler for skimmings **Limepor SK**. The thickness of the finish will be maximum 1 mm with a maximum consumption of materials in both layers of 1.3 kg/m².