

## Skimming of interior or exterior plasters with skimming coat (max granulometry 0,6 mm)

LV39\_SA\_EN\_R2-0517

### APPLICATION DATA SHEET

Skimming of interior or exterior plasters with skimming coat (max granulometry 0,6 mm) by:

1. preparation of the substrate;
2. skimming.

#### 1) PREPARATION OF THE SUBSTRATE

In case of old but compact plasters, clean them to remove old paints and flimsy parts (which could compromise the good anchoring) with a suitable pressure washing and, where necessary, with mechanical abrasions, in order to eliminate old paints and inconsistent parts that could compromise the good anchoring of the subsequent layers. On new plaster, wait until it is completely cured and check that it is compact and clean.

Then wet the substrate to saturation.

#### 2) SKIMMING

Apply the product in two layers with a metal spatula with **Limepor EDO** (white). The thickness of the finish will be 2 mm with a maximum consumption of materials in both layers of 3 kg/m<sup>2</sup>.