

Exposed waterproofing of balconies and terraces, even already tiled, with elastic cementitious systems

LV81_SA_EN_R4-0617

APPLICATION DATA SHEET

Exposed waterproofing of balconies and terraces, even already tiled, with elastic cementitious systems prior:

1. preparation of the substrate;
2. waterproofing;
3. protective coat.

1) PREPARATION OF THE SUBSTRATE

Refer to the Application Data Sheet "Preparation of substrates to be waterproofed" ([LV80](#)) for what concerns the cleaning of the substrate; preliminary checks; preparation of the substrate; and check and restoration of joints and connecting gutters.

In correspondence with the joints, place preformed plastic cord in closed polyethylene foam **Ethafoam**, which prevents the adherence of sealant to the bottom of the joint (in the case of joints larger than 5 mm) and sealing with polyurethane sealant **Tecnoseal 130**.

In the case of screeds or laying on glazed tiles, spread with a brush or roller **Kimicover FIX MV** respecting the consumption rate indicated in the Technical Data Sheet, without covering the previously positioned sealant.

Apply **Kimicover JOINT** and **Kimicover JOINT P**, in correspondence with joints, cuffs and drains.

Proceed with waterproofing of joints, cuffs and drains using **Kimicover GUAINA** applied with brush or roller on the mesh **Kimitech 120** laid in correspondence with joints, cuffs and drains.

2) WATERPROOFING

On the surface to be waterproofed, clean and sound, pour **Kimicover GUAINA** and spread it with a steel trowel or a plaster.

Place mesh **Kimitech TNT** immediately, making sure that it adheres to the membrane using a trowel or a plaster (in case of overlapping, overlap it for a 20 cm length).

Pour another layer of **Kimicover GUAINA** on the reinforcement mesh to improve the waterproofing. Between the following 24 and 48 hours, apply a layer of finish **Kimicover GUAINA**. In order to know the overall consumption of **Kimicover GUAINA (A+B)** in all procedures, consult the Technical Data Sheet.

3) FINAL PROTECTIVE COAT

Once the last **Kimicover GUAINA** layer's curing is complete, (1-2 days at 20°C; 10-15 days at 5°C) proceed with the laying by brush or roller of **Kimicover BLINDO**, following the consumption of 0,3 Kg/m².

The resin, once cured, will have an anti-slip and anti-reflective surface with excellent resistance to atmospheric agents, freeze-thaw cycles and acid rain.