



Antieaporante W

ST2-0217

Film-forming curing agent for concrete castings.



DESCRIPTION

Curing agent in aqueous emulsion creating a uniform film on the concrete, slightly elastic, impermeable to water and air. Type 1 system, according to UNI 8656.

ADVANTAGES

- **Performing:** improves mechanical strength and avoid concrete degradation. Reduces surface dustiness. Reduces plastic shrinkage cracks.
- **Easy to apply:** reduce manpower time and cost than traditional castings protection systems (water, plastic sheets, wet jute bags).

USES

The curing agent is used for the protection of freshly made concrete castings from rapid evaporation of water due to sun and wind. It is particularly suitable for works such as industrial flooring, external flooring airport runways, plasters of dams, bridges, canals and tanks.

APPLICATION

	Paint roller or brush application		Mechanical device application
--	-----------------------------------	---	-------------------------------

The application has to be made over the concrete surface after water evaporation, after curing starting, (for industrial flooring) or after the formwork removal (for concrete).

The product has to be laid (by roller or spray) in one coat, creating a thin and uniform layer. Protect the treated areas for at least 2-3 hours from the washout action due to possible rainfalls.

PACKAGING

Tap. 25 Kg
Pallet – 24x25 Kg – 600 Kg

CONSUMPTION

0,15-0,20 Kg/mq

STORAGE

Protect from humidity. Product, stored in a dry, sheltered place, maintains its technical features for 12 months.

WARNING

Products intended for professional use.
The curing agent prevents the adhesion of any other finishing products.
Its use is not recommended to cure concrete or plasters if afterwards finishings or paintings are expected.
Subsequent coatings may be applied after mechanical removal of the product from the surface through bush-hammering or sandblasting.
Horizontal surfaces (roads, parking lots, airports runways) treated with Antieaporante W may be slippery for wheeled vehicles in transit.

The technical specifications and application methods recommended here are based on our current knowledge and experience and do not represent any form of guarantee over the final results with the products.

The customer is responsible for checking that this data sheet is still effective and it has not been replaced by an updated version.