

## Kimicover FIX MV

ST7-0619

*Bicomponent medium-viscosity epoxy resin used for the preparation of substrates before waterproofing with Kimicover resins.*



### DESCRIPTION

**Kimicover FIX MV** is a two-component, medium viscosity epoxy primer used in the case of waterproofing on highly alkaline screeds, extremely humid when applying the waterproofing membrane and/or due to infiltrations caused by application deficiencies (incorrect treatment of joints and lapels).

It is supplied in two pre-dosed containers (A + B resin, hardener).

It is CE marked as a protective coating according to 1504-2 for intervention principles MC and IR.

### ADVANTAGES

- **Performing:** allow the application of waterproofing systems even on humid substrates.
- **Easy to apply:** can be applied by roller or brush

### USES

**Kimicover FIX MV** is used for:

- treatment of new screeds;
- treatment of existing screeds realised on bituminous membranes

### APPLICATION

	Roller or brush application		Complete hardening time: 7 days
--	-----------------------------	---	---------------------------------

To prepare the product add component A to component B and mix accurately with a low speed drill (200-300 spins/min) until you get a perfect mixture.

**Kimicover FIX MV** must be applied on mechanically consistent and properly prepared substrates (without paints, dust, oils, incoherent and/or detaching parts).

Lay the product by brush or roll, taking into consideration the fact that the next layers should be made between the next 6 and 36 hours.

### CONSUMPTION

0,2-0,6 Kg/m<sup>2</sup> according to the substrate porosity

### PACKAGING

Con 6 kg (Resin: 1,3 Kg – Hardener: 4,7 Kg)  
Pallet 100x6 – 600 Kg

### STORAGE

The product fears humidity. In sealed cans and in a dry place the product maintains its stability for 24 months.

Characteristics	Value
Color	Red
Mixture consistency	Fluid paste
Workability time	60 mins
Viscosity type Brookfield (300 r.p.m. e 25°C) UNI 8490-3	100 - 120 mPa·s
Frost time	1h
Glass transition temperature $T_g$ EN 12614	+77 °C
Complete hardening	7 days
Min temperature of application	+ 5 °C

### WARNING

Product intended for professional use.

In case the substrate is dusty or crumbly please contact our Technical Office.

Do not apply the product with forecast of imminent rain, in presence of fog and dew or with temperature below +5°C. The tools used for the preparation and laying of the product should be cleaned with water before hardening.

**Kimicover FIX MV** must be handled with care: use gloves, protection creams and glasses to avoid contact with skin and eyes. In case of contact with eyes wash abundantly with hot water and seek medical advice.

The technical specification and application methods recommended herein are based on our current knowledge and experience and do not represent any form of

guarantee of the final result obtainable with the product.  
It is the customer's responsibility to check that the product is suitable for the intended use and that this data sheet is still effective and has not been replaced by a more recent version.